# Cem-Dye<sup>™</sup> (W) WB 501 System

SYSTEM DATASHEET

## SYSTEM DESCRIPTION

Cem-Dye (W) WB 501 is a liquid concrete dying system offering a broad color pallet, ranging from soft earth tones to strong vivid tones. This color range can be used to create striking flooring systems that cannot be achieved using reactive acid-based staining systems. Since extensive cleaning and neutralization is not required after the staining process, projects can be completed more economically. Cem-Dye (W) WB 501 System is ideal for interior residential and commercial spaces.

#### **FEATURES & BENEFITS**

- Chemical resistant
- Abrasion resistant
- Impact resistant
- Exceptional durability
- Low VOC
- Qualifies for LEED projects
- Available in a satin finish

### **PRODUCTS**

- Cem-Dye<sup>™</sup> (W)
- SK-E200
- SK-P501

### **SYSTEM USES**

Cem-Dye (W) WB 501 system is designed for use on interior, conventional and architectural concrete.

#### **COLORS**

Available in 16 standard colors.

PHYSICAL PROPERTIES	
Gloss (60 degrees)	90
Gloss (Satin material, 60 degrees)	50-60
Pendulum hardness (ASTM D 4336)	175
Flexibility ASTM D 222	Passes 1/8"
Impact Resistance ASTM D 2749	Passes 3/8"- inch-pound direct impact
Tabor Abrasion (1000 gm, load 1000 cycles CS 17 wheel)	32 mg. loss
Adhesion to concrete ASTM D 451	Concrete fails before loss of bond
Volatile Organic Compounds	100 grams/liter

## SURFACE PREPARATION

Surface must be clean, dry and profiled prior to installation. Acceptable methods for preparation are diamond grinding or acid etching. If acid etching, follow APF written instructions. Concrete must have a minimum surface profile ICRI CSP 2, or a texture similar to 120-arit sandpaper.

# **CHEMICAL RESISTANCE**

Please refer to the Arizona Polymer Flooring Chemical Resistance Guide for fully system chemical resistance.

# **INSTALLATION**

Please refer to the "Cem-Dye (W) WB 501 System Application Instructions" for information on installing this system.





# Cem-Dye<sup>™</sup> (W) WB 501 System

SYSTEM DATASHEET

# MOISTURE VAPOR EMISSIONS PRECAUTIONS:

All concrete floors not poured over an effective moisture vapor retarder are subject to possible moisture vapor transmission that may lead to blistering and failure of the coating system. It is the coating applicator's responsibility to conduct calcium chloride testing in compliance with ASTM F1869, or relative humidity probe testing in compliance with ASTM-F2170, to determine if excessive levels of vapor emissions are present before applying any coatings. Arizona Polymer Flooring offers S-1300 Pene-Krete® for cementitious overlay products and VaporSolve® Moisture Remediation systems for resinous floor coatings. Consult our technical service department. Arizona Polymer Flooring and its sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

#### **WARRANTY:**

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.



