

LIMITATIONS:

- Material must be mixed mechanically for proper performance.
- Application rate must be kept above 200 sq. ft. per gallon to avoid curing bubbles that occur in thicker applications.
- Applications over textured surfaces such as trowel-knockdown polymer concrete must be done with a 3/4" nap roller and pulled tightly to avoid leaving excessive product in recessed areas.
- Work life is considerably shortened over 90 degrees F.
- Do not apply material if the humidity is over 90% and ventilation is poor. Improper cure will result.

WARRANTY:

Arizona Polymer Flooring guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ARIZONA POLYMER FLOORING MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. Arizona Polymer Flooring shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. Arizona Polymer Flooring shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.

Super-Krete® Products is a Division of Arizona Polymer Flooring, Inc.

© 2017 Arizona Polymer Flooring, Inc

4565 W Watkins St. / Phoenix, AZ 85043 / 800.562.492

623.435.2277 Tel. / 623.435.8585 Fax

www.super-krete.com

SK-P501 032717

